
This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of
the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
 - TEXT CUT OFF AT TOP, BOTTOM OR SIDES
 - FADED TEXT
 - BLURRY OR ILLEGIBLE TEXT
 - SKEWED/SLATED IMAGES
 - COLORED PHOTOS
-
- BLACK OR VERY DARK BLACK AND WHITE PHOTOS
 - UNDECIPHERABLE GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PATENT COOPERATION TREATY

PCT

NOTIFICATION OF ELECTION

(PCT Rule 61.2)

From the INTERNATIONAL BUREAU

To:

Assistant Commissioner for Patents
United States Patent and Trademark
Office
Box PCT
Washington, D.C.20231
ETATS-UNIS D'AMERIQUE

in its capacity as elected Office

Date of mailing (day/month/year) 18 October 2000 (18.10.00)	
International application No. PCT/EP00/01900	Applicant's or agent's file reference 4685/KH
International filing date (day/month/year) 06 March 2000 (06.03.00)	Priority date (day/month/year) 16 March 1999 (16.03.99)
Applicant ADRIAENSEN, Ludo et al	

1. The designated Office is hereby notified of its election made:

☒ in the demand filed with the International Preliminary Examining Authority on:

18 September 2000 (18.09.00)

☐ in a notice effecting later election filed with the International Bureau on:
2. The election ☒ was
☐ was not

made before the expiration of 19 months from the priority date or, where Rule 32 applies, within the time limit under Rule 32.2(b).

The International Bureau of WIPO 34, chemin des Colombettes 1211 Geneva 20, Switzerland Facsimile No.: (41-22) 740.14.35	Authorized officer Charlotte ENGER Telephone No.: (41-22) 338.83.38
---------------------------------------------------------------------------------------------------------------------------------------	-----------------------------------------------------------------------------------

PATENT COOPERATION TREATY

PCT

INTERNATIONAL SEARCH REPORT

(PCT Article 18 and Rules 43 and 44)

Applicant's or agent's file reference 4685/KH	FOR FURTHER ACTION see Notification of Transmittal of International Search Report (Form PCT/ISA/220) as well as, where applicable, item 5 below.	
International application No. PCT/EP 00/ 01900	International filing date (day/month/year) 06/03/2000	(Earliest) Priority Date (day/month/year) 16/03/1999
Applicant N.V. BEKAERT S.A.		

This International Search Report has been prepared by this International Searching Authority and is transmitted to the applicant according to Article 18. A copy is being transmitted to the International Bureau.

This International Search Report consists of a total of 2 sheets.

☒ It is also accompanied by a copy of each prior art document cited in this report.

1. Basis of the report

- a. With regard to the **language**, the international search was carried out on the basis of the international application in the language in which it was filed, unless otherwise indicated under this item.

☐ the international search was carried out on the basis of a translation of the international application furnished to this Authority (Rule 23.1(b)).

- b. With regard to any **nucleotide and/or amino acid sequence** disclosed in the international application, the international search was carried out on the basis of the sequence listing :

☐ contained in the international application in written form.

☐ filed together with the international application in computer readable form.

☐ furnished subsequently to this Authority in written form.

☐ furnished subsequently to this Authority in computer readable form.

☐ the statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.

☐ the statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished

2. ☐ **Certain claims were found unsearchable** (See Box I).

3. ☐ **Unity of Invention is lacking** (see Box II).

4. With regard to the **title**,

☒ the text is approved as submitted by the applicant.

☐ the text has been established by this Authority to read as follows:

5. With regard to the **abstract**,

☒ the text is approved as submitted by the applicant.

☐ the text has been established, according to Rule 38.2(b), by this Authority as it appears in Box III. The applicant may, within one month from the date of mailing of this international search report, submit comments to this Authority.

6. The figure of the **drawings** to be published with the abstract is Figure No.

☒ as suggested by the applicant.

☐ because the applicant failed to suggest a figure.

☐ because this figure better characterizes the invention.

1

☐ None of the figures.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/01900

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D06N7/00 D04H3/04 E04H15/54

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D06N D04H E04H D03D B32B B60J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98 55682 A (VANDEWALLE GERARD ;BEKAERT SA NV (BE); ADRIAENSEN LUDO (BE)) 10 December 1998 (1998-12-10) cited in the application the whole document	1-3, 11-13, 16, 19, 20
A	GB 2 317 363 A (C M I) 25 March 1998 (1998-03-25)	
A	EP 0 441 719 A (TISSUS TECH DE TREVoux) 14 August 1991 (1991-08-14)	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

21 June 2000

Date of mailing of the international search report

28/06/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Rebiere, J-L

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 00/01900

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9855682	A	10-12-1998	AU 8019298 A EP 0986668 A ZA 9804263 A	21-12-1998 22-03-2000 30-11-1998
GB 2317363	A	25-03-1998	NONE	
EP 0441719	A	14-08-1991	FR 2657894 A FR 2663965 A AT 135967 T CA 2033797 A DE 69118225 D DE 69118225 T US 5213874 A	09-08-1991 03-01-1992 15-04-1996 07-08-1991 02-05-1996 05-09-1996 25-05-1993




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : D06N 7/00, D04H 3/04, E04H 15/54</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/55419 (43) International Publication Date: 21 September 2000 (21.09.00)</p>
<p>(21) International Application Number: PCT/EP00/01900 (22) International Filing Date: 6 March 2000 (06.03.00) (30) Priority Data: 99200806.0 16 March 1999 (16.03.99) EP (71) Applicant (for all designated States except US): N.V. BEKAERT S.A. [BE/BE]; Bekaertstraat 2, B-8550 Zvegem (BE). (72) Inventors; and (75) Inventors/Applicants (for US only): ADRIAENSEN, Ludo [BE/BE]; Bottenhoek 14, B-8540 Deerlijk (BE). VANDEWALLE, Gerard [BE/BE]; Oliebergstraat 46, B-8540 Deerlijk (BE).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report.</p>

(54) Title: CANVASSES REINFORCED WITH METAL MEMBERS

(57) Abstract

The invention relates to a fabric (10) for reinforcement of canvasses. The fabric comprises a warp (12) and a weft (14). At least one of the warp or the weft is formed by a strip comprising at least one elongated metal member (18) and a thermoplastic material (22) as matrix. A primer layer (20) is applied on the metal member before the application of the thermoplastic material to obtain a good adhesion between the thermoplastic material and the metal member.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Canvasses reinforced with metal members**Field of the invention.**

5 The present invention relates to a fabric and to a strip for the reinforcement of canvasses having a plastic coating.
The invention also relates to the use of a fabric and a strip for the reinforcement of canvasses having a plastic coating.

Background of the invention.

10 Canvasses with a plastic coating are for example used to cover the loads on vehicles or containers, they are also used as tent material.

Such canvasses must meet several requirements.

15 They must be sufficient strong to avoid tearing due to movement of the load and simultaneously they must be sufficient flexible so that the canvasses can be easily and quickly slid to one side to open them.

A further requirement is that they must give a good protection against vandalism and robbery. Therefore a high resistance against the action of a knife or against the action of a pair of scissors is required.

20 Since the weight of the canvass limits the amount of load that may be transported by the vehicle or container, the weight of the canvass must be as low as possible.

WO 98/55682 describes a fabric for the reinforcement of canvasses.

25 This reinforcement consists of strips comprising a thermoplastic matrix and several parallel metal members.

This gives a good flexibility and a rather good resistance against the action of a knife or a cutter. The resistance against the action of a pair of scissors achieved by this embodiment is not always sufficient.

30

Summary of the invention.

It is an object of the invention to provide a fabric for the reinforcement of canvasses having an improved resistance against the action of a knife or a cutter and against the action of a pair of scissors or a pair of shears.

35 It is a second object to provide a fabric with a good corrosion resistance.

It is a further object to provide a fabric with a low weight.

-2-

According to one aspect of the invention, there is provided a fabric for the reinforcement of canvasses, having a plastic coating.

The fabric comprises a warp and a weft. At least one of the warp or the weft is formed by a strip comprising at least one elongated metal member and a matrix of a thermoplastic material. The thermoplastic material is adherable to the plastic coating of the canvas. A primer layer is applied on the metal member before the thermoplastic material is applied on said coated metal member to realise a good adhesion between the thermoplastic material and the metal member.

The strips have a cross-sectional thickness ranging from 0.5 mm to 3 mm and a cross-sectional width ranging from 3 mm to 25 mm, preferably the thickness is between 0.5 mm and 2 mm and the width is between 3 mm and 15 mm.

The strips forming the warp and the strips forming the weft form meshes with a maximum dimension ranging from 5 cm to 30 cm. The dimension of these meshes can be adapted to the kind of goods that has to be transported. In most cases a maximum dimension of about 7 cm to 15 cm is preferred.

The strips forming the weft can be welded to the strips forming the warp or they can be fixed to each other by means of an adhesive.

According to a second aspect of the invention, there is provided a strip for reinforcement of canvasses having a plastic coating.

The strip comprises at least one elongated metal member and a matrix of a thermoplastic material. The thermoplastic material is adherable to the plastic coating of the canvas. A primer layer is applied on the metal member. This primer layer is required to obtain a good adhesion of the thermoplastic material to the metal member. Such a primer layer is applied on the surface of the metal member before the application of the thermoplastic material.

When no primer layer is applied, the wire could be pulled out the strip without difficulties.

-3-

Further, without the application of such a primer layer, the thermoplastic material, such as PVC (polyvinylchloride) flows away during the welding of the strip on the canvass. In this case the metal member is not longer surrounded by the matrix material after the welding. This would result in a fabric which is susceptible of corrosion.

5 Preferably, the primer layer maintains its adhesion characteristics even if the material is subjected to a heat treatment, for example during the welding of the strips on the canvass.

Therefore, the primer layer preferably withstand a heat treatment during some minutes, for example 5 minutes at 150 °C without losing its characteristics.

15 The application of a primer layer on the metal further allows it to reduce the thickness of layer of the thermoplastic material. This is of great importance since the amount of thermoplastic material used, has a direct influence on the weight of the reinforced canvass. As described before, it is desirable that the weight of the canvass is as low as possible.

20 The metal member must give the strip the required strength but must also enable the strip to remain sufficient flexible, preferably in all directions. The flexibility of the strip is strongly influenced by the type of metal member used to reinforce the strip.

25 The metal member is preferably a flat wire. Flat wire is flexible in the direction perpendicular to the flat side of the wire.

Since the flexibility is determined by the thickness of the wire, the wire is preferably less than 0.40 mm, more preferably less than 0.35 mm, for instance less than 0.30 mm.

30 Since the resistance against the action of a pair of scissors is increased when the tensile strength is high, a tensile strength of at least 1500 N/mm² is preferred, more preferably the tensile strength is greater than 1700 N/mm².

To obtain the desired tensile strength a carbon content greater than 0.40 % is preferred.

-4-

By preference, the wire is rounded off so that the cross section has no sharp corners, which could result in a damage of the canvass during welding.

5 Another metal member that can be used is a wire with a rounded I-profile. An I-profiled wire is a wire with a cross section resembling an I-shape. The thickness of the left end and the thickness of the right end are greater than the center thickness of the wire.

10 This wire has the same flexibility as a flat wire with a thickness equal to the center thickness of the I-profiled wire. The resistance against the action of a pair of scissors of this I-profiled wire is improved in comparison with this flat wire. This resistance equals the resistance of a flat wire with a thickness equal to the thickness of the broader left and right end of the I-profiled wire while the weight of such an I-profiled wire

15 is reduced compared with this flat wire.

In another embodiment the metal member comprises at least two metal members. These metal members are preferably located parallel in the plane of the strip. The metal members could be round steel wires,

20 square wires, rectangular wires or another type of wires. Each metal member is hereby in contact with at least one other metal member, so that they form together a kind of a flat wire.

25 The plurality of the elongated metal members gives the strip a good flexibility. The resistance against the action of a knife or against the action of a pair of scissors is remained because of the arrangement of the metal members forming a flat wire.

To improve the corrosion resistance of the fabric, the metal member or the metal members can be coated with a metallic coating layer such as

30 zinc or a zinc alloy comprising 2 to 10 % Al and 0.1 to 0.4 % of a rare earth element such as La and/or Ce.

A thermoplastic material such as PVC (polyvinylchloride) is applied on the metal member. The application can be done by any conventional

-5-

means. Preferred application methods are extrusion, fluidised bed coating or plastisol coating.

5 The adhesion of the primer to the wire surface is improved when the surface of the wire is clean. Therefore, it can be desirable to degrease the wire surface before applying the primer layer.

10 The application of the primer layer may be done by any conventional means.

A first group of primers that can be used are thermosetting materials. Binding agents are thereby dissolved in an organic solvent or are dispersed with a limited amount of a dispersing agent in water to form an emulsion or a suspension.

15 Suitable binding agents are based on acrylate, alkyd/melamine, epoxy or fenol/epoxy resins. Other binding agents giving a good adhesion to the metal and to the PVC compounds can also be used.

Additives such as anticorrosion pigments, wetting agents and/or stabilising agents can be added.

20 The primer composition is applied to the metal by immersing the wire into the solution, the emulsion or the suspension of the primer material; the primer composition can also be applied by spraying.

The thickness of the wet primer layer can be calibrated by passing the wire and the primer through the calibrated opening of a die.

25 Alternatively, the thickness of the primer layer can be calibrated by felt wiping or by air wiping in a controlled air stream.

The thickness of the primer layer may be influenced by further diluting the primer composition.

In order to allow drying and curing, the wire can be heated.

30 Since it is desirable that the weight of the canvass is as low as possible, the thickness of the primer layer must be low. The thickness of the dry primer layer is preferably less than 10 μm , more preferably less than 5 μm , for instance less than 1 μm .

35 Radiation curable resins such as ultra violet, electron beam or infra red curable resins are also suitable as primer.

A second group of primer layers that can be applied are hot melts, for example ethylene copolymers such as EVA (ethyl vinyl acetate), polyamides or polyesters. In order to obtain a sufficient thin layer, it is preferred to use hot melts with a viscosity at 200°C of less than 20 Pa.s, more preferably this viscosity is less than 15 Pa.s. This hot melt can be applied with a variety of different equipments. Very suitable is the melt pot. Also application by extrusion is possible under certain conditions. A method for the application by extrusion is described in the patent specification BE 1006346.

Depending on the viscosity and the method of the application of the primer layer, primer layers with a thickness of less than 25 µm, for instance less than 5 µm are obtained.

A third group are silane-compounds. One functional group of these coupling agents is responsible for the binding with the metal or metal oxides; the other functional group reacts with the polymer.

More details about these silane compound can be found in the PCT application with the application number PCT/BE98/0015. Usually the silane compounds are diluted in alcohols, although they can be diluted in other solvents or in water as well. With this type of compounds very thin primer layers with a thickness of 20 nm or even less can be achieved.

The adhesion between the thermoplastic material and the metal member can be evaluated by carrying out the following test.

The PVC layer is removed in the longitudinal direction over about 5 cm by means of the sharp side of a knife. By means of the blunt side of the knife the PVC layer is slightly lifted. Finally, the synthetic coating is tried to be pulled off the metal member with the fingers.

The more difficult the PVC layer can be pulled off, the stronger the adhesion of the PVC to the metal member.

-7-

The test is carried out both on a wire on which a PVC layer is extruded directly and on a wire coated with a primer layer before the extrusion of the PVC layer.

5 The PVC coating, extruded directly on the metal member can be pulled off easily, while the removal of the PVC coating is much more difficult when a primer layer is applied on the metal member.

10 After the application of the primer layer on the metal member the thermoplastic material is applied on the metal member.

The thermoplastic material must give a good adhesion to the canvass. Since canvasses are usually coated with PVC, the thermoplastic material is preferably a PVC compound, although other thermoplastic materials with a good adhesion to PVC can be used as well.

15 Canvasses can also be made of polypropylene, polyethylene or of polyester. In these cases one chooses a thermoplastic material which gives a good adhesion to this polymers.

Brief description of the drawings.

20 The invention will now be described into more detail with reference to the accompanying drawings wherein

- FIGURE 1 shows a fabric according to the first aspect of the present invention.
- FIGURE 2, FIGURE 3 and FIGURE 4 show three strips
- 25 according to the second aspect of the present invention.

Description of the preferred embodiments of the invention.

Figure 1 shows an embodiment of a fabric according to the first aspect of the invention.

30 This fabric 10 comprises strips forming the warp 12 and strips forming the weft 14. The strips 12 and the strips 14 are welded to each other. The width W of the meshes is 7.5 cm, the height H of the meshes is 15 cm.

Figure 2 shows a strip 16 according to the second aspect of the invention.b

The strip comprises a hard rolled flat steel wire 18 of the type 4.00 x 0.30 mm, with a tensile strength, R_m of 1700 N/mm². The carbon content of the steel is equal to 0.70 %.

On this wire a primer 20 is applied. An alkyd/melamine resin is dissolved in a solvent such as benzene, xylene or in an alcohol. An anticorrosion pigment is added. The composition is about 30 % of the binding agent and about 70 % of the solvent. The primer is once diluted with acetone. After drying and curing a primer layer with a thickness between 0.8 and 2.5 μ m is obtained.

The strip comprises PVC as matrix material 22. This PVC material is applied by extrusion.

The width of the strip equals to 6.00 mm, the thickness is 0.80 mm.

Figure 3 shows another strip 16, comprising a rounded I-profile wire 18'. The wire has a tensile strength, R_m of 1750 N/mm² and a carbon content of 0.80 %. The wire has a width of 4.00 mm. The center thickness is 0.30 mm and the thickness at the left and the right end equals 0.45 mm. This wire has the flexibility of a flat wire with a thickness of 0.30 mm and the resistance against the action of a pair of scissors of a flat wire with a thickness of 0.45 mm.

A primer 20 is applied on this wire. The following composition of the primer is used : about 30 % fenol/epoxy resin, 8 to 10 % alcohol, 2.5 % diethanolamine in water. The thickness of the primer layer after drying and curing ranges between 1 and 4 μ m.

The strip comprises PVC as matrix material 22. The PVC is applied by fluidised bed coating. The strip 16 has at least on one side a flat surface.

The width of the strip is 6.00 mm, the thickness is 0.90 mm.

Figure 4 shows another embodiment of a strip 16 comprising four round steel wires 18'' with a diameter of 0.40 mm.

These wires are located parallel in the plane of the strip 16. Each wire is hereby in contact with his neighbor or neighbors.

-9-

The tensile strength R_m of the wire equals 2550 N/mm²; the carbon content is 0.80 %.

A primer layer is applied on the wires. The strip comprises PVC as matrix material 22. The strip has at least on one side a flat surface.

5 The width of the strip is 5.00 mm, the thickness is 0.80 mm.

CLAIMS

1. A fabric (10) for reinforcement of canvasses having a plastic coating,
said fabric comprising a warp (12) and a weft (14), at least one of the
warp or the weft being formed by a strip which comprises at least one
elongated metal member (18) and a matrix of a thermoplastic
material (22) adherable to the plastic coating of the canvasses,
characterised in that said elongated metal member has been coated
with a primer layer (20) before said thermoplastic material is applied
on the coated metal member to realise an adhesion between said
thermoplastic material and said elongated metal member.
2. A fabric according to claim 1, whereby both the warp and the weft
are formed by said strip.
3. A strip (16) for reinforcement of canvasses having a plastic coating,
said strip comprises at least one elongated metal member (18) and a
matrix of a thermoplastic material (22) adherable to the plastic
coating of the canvasses extruded on the metal member,
characterised in that said elongated metal member has been coated
with a primer layer (20) before said thermoplastic material is
extruded on the coated metal member to realise an adhesion
between said thermoplastic material and said elongated metal
member.
4. A strip according to claim 3, whereby said primer layer comprises a
thermosetting material.
5. A strip according to claim 4, whereby said thermosetting material is
selected from the group consisting of acrylate based resins, epoxy
based resins or alkyd based resins.
6. A strip according to claim 3, whereby said primer layer comprises a
hot melt.

-11-

7. A strip according to claim 6, whereby said hot melt is selected from the group consisting of ethylene copolymers, polyamides or polyesters.
- 5 8. A strip according to claim 3, whereby said primer layer comprises a bifunctional silane compound.
9. A strip according to anyone of claims 3 to 8, whereby said thermoplastic material is polyvinylchloride.
- 10 10. A strip according to anyone of claims 3 to 8, whereby said thermoplastic material is a polyvinylchloride compound.
11. A strip according to anyone of claims 3 to 10, whereby said metal member is a flat wire with a tensile strength greater than 1500 N/mm².
- 15 12. A strip according to anyone of claims 3 to 10, whereby said metal member is a flat wire with a tensile strength greater than 1700 N/mm².
- 20 13. A strip according to anyone of claims 3 to 12, whereby said metal member is a flat wire with a thickness of less than 0.35 mm.
- 25 14. A strip according to anyone of claims 3 to 10, whereby said metal member is a wire with a rounded I-profile.
15. A strip according to anyone of claims 3 to 14, whereby said metal member is a steel wire with a carbon content of at least 0.40 %.
- 30 16. A strip according to anyone of claims 3 to 10, whereby said metal member comprises at least two metal members.

-12-

17. A strip according to claim 16, whereby the metal members are located parallel in the plane of the strip, each metal member being in contact with a least one other metal member.
- 5 18. A strip according to anyone of claims 3 to 17, whereby said metal member is coated with a zinc layer or with a zinc alloy layer.
19. Use of a fabric according to claims 1 or 2 for reinforcement of a canvass.
- 10 20. Use of a strip according to anyone of claims 3 to 18 for reinforcement of a canvass.




Fig. 1




Fig. 2




Fig. 3




Fig. 4

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/01900

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 D06N7/00 D04H3/04 E04H15/54

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 IPC 7 D06N D04H E04H D03D B32B B60J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98 55682 A (VANDEWALLE GERARD ;BEKAERT SA NV (BE); ADRIAENSEN LUDO (BE)) 10 December 1998 (1998-12-10) cited in the application the whole document	1-3, 11-13, 16,19,20
A	GB 2 317 363 A (C M I) 25 March 1998 (1998-03-25)	
A	EP 0 441 719 A (TISSUS TECH DE TREVoux) 14 August 1991 (1991-08-14)	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

*** Special categories of cited documents :**

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

21 June 2000

Date of mailing of the international search report

28/06/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Rebiere, J-L

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/EP 00/01900

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9855682 A	10-12-1998	AU 8019298 A EP 0986668 A ZA 9804263 A	21-12-1998 22-03-2000 30-11-1998
GB 2317363 A	25-03-1998	NONE	
EP 0441719 A	14-08-1991	FR 2657894 A FR 2663965 A AT 135967 T CA 2033797 A DE 69118225 D DE 69118225 T US 5213874 A	09-08-1991 03-01-1992 15-04-1996 07-08-1991 02-05-1996 05-09-1996 25-05-1993